



DO THE JOB RIGHT.®

# RUST ENCAPSULATOR®

## MATTE BLACK FINISH



- Apply Directly Over Surface Rust
- Top Coat with Almost Any Paint or Use as a Top Coat
- Prevents Rust From Spreading
- Penetrates Deep and Cures Fast



Scan for product info

**EASTWOOD RUST ENCAPSULATOR®** is a high-performance coating that encapsulates rust and provides long term protection against corrosion build-up. RUST ENCAPSULATOR can be used as a top coat or can be top coated with almost any paint. It can be applied over bare metal or surface rusted areas. It is epoxy-fortified for excellent adhesion & fast curing, and has been tested to 500 hours in a salt spray chamber. RUST ENCAPSULATOR is ideal for any type of rusted metal surface and can withstand temperatures up to 400°F.

### DIRECTIONS – READ ALL INSTRUCTIONS BEFORE USING THIS PRODUCT!

1. Ensure that the surface is free of all loose rust, scale, and paint – cleaning with a stiff wire brush should be sufficient.
2. Remove all dust, oil, grease, or chemical contamination using EASTWOOD PRE Painting Prep (#10041Z or #11949Z). Allow to dry thoroughly.
3. When applying EASTWOOD RUST ENCAPSULATOR to a patch area, feather the edges of the surrounding paint with 220 grit wet/dry sandpaper. Be sure to feather into the surrounding paint by at least 1-1/4".
4. Shake can well and listen for rattle of mixing ball. Continue to shake for at least 2 minutes. Shake for 10 seconds at 1 to 2 minute intervals during application.
5. Hold can 10 to 12 inches from the surface and apply a medium coat to ensure maximum adhesion, overlapping surrounding paint by at least 1-1/4".
6. Single coats of EASTWOOD RUST ENCAPSULATOR will be touch dry in 20 minutes and thoroughly dry in 3-4 hours at 68°F. If a second coat is desired for greater durability, allow 1 hour before applying the second coat. If applying heavy coats, allow extra drying time before applying. **IMPORTANT:** To keep nozzle clean, remove any build-up on tip after use with lacquer thinner.
7. If applying a top coat, allow at least 6-8 hours drying time. For maximum top coat adhesion, sand the surface with 320 grit wet/dry sandpaper. Allow an extra hour drying time if wet sanding.
8. For best results, top coating should be done within 36 hours of EASTWOOD RUST ENCAPSULATOR application. After 36 hours, be sure to scuff the surface with 320 grit wet/dry sandpaper before top coating.

**IMPORTANT:** To prevent clogging, after each use, invert the can and spray a few short blasts.

**CONTAINS:** 4-Chlorobenzotrifluoride (CAS #98-56-6), Propane (CAS #74-98-6), Acetone (CAS #67-64-1), N-Hexane (CAS #110-54-3), Barium Sulfate (CAS #7727-43-7), N-Butyl Acetate (CAS #123-86-4), Methyl N-Propyl Ketone (CAS #107-87-9), and Carbon Black (CAS #1333-86-4). 59% of the ingredients have an unknown acute toxicity.



**DANGER:** Extremely flammable aerosol. Contains gas under pressure; may explode if heated. Causes skin and serious eye irritation. May cause an allergic skin reaction. May cause respiratory irritation. May cause drowsiness or dizziness. Suspected of causing cancer. Suspected of damaging fertility or the unborn child. May cause damage to organs through prolonged or repeated exposure.

**PRECAUTIONARY STATEMENTS:** Do not handle until all safety precautions have been read and understood. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Do not spray on an open flame or other ignition source. Do not pierce or burn, even after use. Do not breathe spray. Wash hands thoroughly after handling. Use only outdoors or in a well-ventilated area. Contaminated work clothing must not be allowed out of the workplace. Wear protective gloves and eye protection. Protect from sunlight. Store in a well-ventilated place. Do not expose to temperatures exceeding 50°C / 120 °F. Dispose of contents and container in accordance with applicable regulations.

**FIRST AID:** If exposed or concerned or feel unwell: Call a physician. **IF ON SKIN:** Wash with plenty of water. If skin irritation or rash occurs: Get medical advice. Take off contaminated clothing and wash it before reuse. **IF INHALED:** Remove person to fresh air and keep comfortable for breathing. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical advice.

**VOC CONTENT – ABP Maximum MIR 0.90**


**KEEP OUT OF REACH OF CHILDREN**

**WARNING:**  
**Cancer and Reproductive Harm**  
[www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)

Only in the event of a chemical emergency involving a spill, leaks, fire, or exposure call Chemtrec toll-free day or night: 1-800-424-9300 International call collect: (202) 483-7616

Manufactured for The Eastwood Company, 263 Shoemaker Road, Pottstown, PA 19464  
USA: 1-800-343-9353 Canada: 1-800-820-9042  
International: (610) 323-2200 [www.eastwood.com](http://www.eastwood.com)

© Copyright 2017 Easthill Group, Inc. Made in USA Label #16060ZL 4/17 Rev 1



**DANGER:**  
**CONTENTS EXTREMELY FLAMMABLE AND UNDER PRESSURE.**  
Read Precautions On Rear Panel Before Use.

Net wt. 15 oz. / 425 grams

16060Z