



DO THE JOB RIGHT.®

50-STATE COMPLIANT

OEM SELECT BASECOAT

- Low 2.1 VOC
- Excellent Flow with a Fast Dry Time
- Use with Eastwood OEM Select Primers and Clearcoats

FOR INDUSTRIAL USE ONLY by professional, trained painters. Not for sale to or use by the general public.

KEEP OUT OF REACH OF CHILDREN.
NET CONTENTS: 1 Quart (32oz.)

EASTWOOD OEM SELECT BASECOAT PAINT is a low VOC solvent basecoat paint system that is 50 state compliant. This system will provide an exceptional optical effect, high durability, chemical resistance and a lasting finish. All Eastwood OEM Select Basecoat colors should be topcoated with Eastwood OEM Select Clear Coats. It is recommended to use only Eastwood OEM Select Primers, Basecoats and Clearcoats but if you would like to use a different primer or clearcoat we would recommend that you make some test panels first. Shelf life of this paint is 2 years from the date it was mixed.

CONTAINS: Acetone (67-64-1), Butyl acetate (123-86-4), 4-chloro-a,a,a-trifluorotoluene (98-56-6), Xylene (1330-20-7), n-Butanol (71-36-3).
DANGER. HAZARD: Highly flammable liquid and vapor. Harmful in contact with skin. Harmful if inhaled. Causes skin irritation. Causes serious eye irritation. May cause drowsiness or dizziness. Repeated exposure may cause skin dryness or cracking. **PRECAUTIONARY:** Keep away from heat / sparks / open flames/hot surfaces. No smoking. Do not breathe dust / fume / gas / mist / vapors / spray. Wear protective gloves / protective clothing / eye protection/face protection. **IF ON SKIN (or hair):** Remove/Take off immediately all contaminated clothing. Rinse skin with water / shower. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Dispose of contents /container to an authorized waste collection point. See Safety Data Sheet. **KEEP OUT OF REACH OF CHILDREN.**

Mixing ratio in volume parts	Number of coats/ film build	Flash-off time	Drying time:
1:1 with Reducer	2 - 3 0,6 - 1 mil	10 - 15 mins @ 68°F	15 - 20 mins @ 68°F

WARNING: This product can expose you to chemical(s) which are known to the State of California to cause cancer or birth defects or other reproductive harm. For more information, visit www.P65Warnings.ca.gov



APPLICATION INSTRUCTIONS:

1. Remove any rust or surface defects and complete all body work needed.
2. Use Eastwood OEM Select Primers to prep the surface for color. Follow the instructions on the primer label for proper primer application.
3. Use Eastwood PRE Painting Prep to completely clean the area of all oils, dirt or grease.
4. If you are using 100% Basecoat you will need to mix enough paint and reducer to complete your project. Mix Basecoat 1:1 with Eastwood OEM Select Reducer and stir until blended completely. If you are using OEM Select Ready to Spray (RTS) Basecoat you can still reduce up to 10% of the volume to get the consistency best suited for your paint equipment/environment.
5. Apply paint with a good quality HVLV spray gun with a 1.3 - 1.4mm Nozzle Size. Starting air pressure at the gun inlet should be 30-45 psi and adjusted as needed. 2-3 coats should be applied. Flash time in between coats should be 5-15 minutes or until matte. Coating Thickness at 2-3 coats will be 0.6-1 mil.
6. Once paint application is complete the final flash off time should be 10-15 minutes at 68°F. An additional drying time of 15-20 minutes at 68°F would be required for touch. Taping can be performed at 20-45 minutes of dry time depending on temperature and humidity of the day.

Only in the Event of a Chemical Emergency Involving A Spill, Leaks, Fire, or Exposure Call Chemtrec

Toll Free Day or Night: 1-800-424-9300 International Call Collect: (202) 483-7616

Manufactured for The Eastwood Company, 263 Shoemaker Road, Pottstown, PA 19464
1-800-343-9353 www.eastwood.com © Copyright 2022 Eastwood Automotive Group LLC Label #59122QTZPLBL Rev 1

