

CONTAINS: Water 7732-18-5, Acrylic Copolymer Latex (Proprietary), 2-Butoxethanol 111-76-2, Tannic Acid 1401-55-4, Ethylene Glycol 107-21-1.

See MSDS for complete safety information.

CAUTION: May be harmful if swallowed. Avoid contact with eyes and mucous membranes. Avoid prolonged or repeated contact with skin. Use with adequate ventilation.

FIRST AID

IF SWALLOWED: Contact physician or poison center immediately. Rinse mouth with water and give person 1 to 2 glasses of water. Never give anything by mouth to an unconscious person.

IF IN EYES: Flush eyes with water for at least 15 minutes. If irritation is persistent, contact a physician.

IF ON SKIN: Wash skin with soap and water. Remove all contaminated clothing and launder separately before reuse. If irritation is persistent, contact a physician.

IF INHALED: Remove person to fresh air.

KEEP OUT OF THE REACH OF CHILDREN

Only in the Event of a Chemical Emergency Involving
A Spill, Leaks, Fire, or Exposure Call Chemtrec
Toll Free Day or Night: 1-800-424-9300
International Call Collect: (202) 483-7616

Manufactured for The Eastwood Company,
263 Shoemaker Road, Pottstown, PA 19464
USA: 1-800-345-1178 Canada: 1-800-820-9042
International: (610) 323-2200 www.eastwood.com
© Copyright 2011 Easthill Group, Inc. Made in USA
Label #5167ZPL Rev. 4/12



Scan for product info



DO THE JOB RIGHT.

RUST CONVERTER



- Transforms Rust Into a Paintable Surface
- Eliminates Need for Sanding
- Compatible with Most Top Coats

**CAUTION! MAY BE HARMFUL IF SWALLOWED.
KEEP OUT OF REACH OF CHILDREN.**

(See additional precautionary statements on back panel)

Net Contents. 1 Gallon / 128 fl. oz. **51677 ZP**

EASTWOOD'S RUST CONVERTER halts residual rust in its tracks and converts the surface to a black protective polymeric coating. This protective coating seals out moisture and can be top coated with most paints. This single component converter can be sprayed or brush applied. One gallon covers about 200-300 square feet on a non-porous smooth surface. Irregular or textured surfaces may require more product. Must be top coated.

D I R E C T I O N S

Please read entire label before using this product.

SURFACE PREPARATION: Use a wire brush or sandpaper to remove all loose rust and scale. USE EASTWOOD'S PRE to remove all residual grease and oils on surface to be treated.

APPLICATION EQUIPMENT: EASTWOOD'S RUST CONVERTER can be applied with an HVLP or conventional spray gun, use a 1.0 to 1.4 nozzle at low pressure for best results. A trigger bottle may also be used – it is recommended that the trigger bottle not be used for any other products or disposed of after use. For brushing, use a common household paint brush or a foam type brush.

APPLICATION: Shake well before using. No dilution or reducing is necessary; this product is most effective right out of the bottle.

Do not apply this product to surfaces that are below 50°F. Do not apply this product to painted surfaces, as damage may occur. Using a brush or spray gun, liberally apply EASTWOOD'S RUST CONVERTER to corroded surface. In about 20 minutes the surface will turn to a dark finish, then apply a second coat and let cure for 48 hours. Temperatures may alter cure times. After 48 hour cure time the surface may be top coated with a paint, or for maximum corrosion resistance, coat with EASTWOOD RUST ENCAPSULATOR, then apply final top coat.

IMPORTANT: DO NOT RETURN UNUSED MATERIAL TO ORIGINAL CONTAINER